



Application Datasheet

Standard Designation for Cast Copper Alloys

- C90000-C91999: Copper-Tin Alloys (*Tin Bronzes*)
- C92000-C92900: Copper-Tin-Lead Alloys (*Leaded Tin Bronzes*)
- C93000-C94500: Copper-Tin-Lead Alloys (*High-Leaded Tin Bronzes*)
- C94600-C94999: Copper-Tin-Nickel Alloys (*Nickel-Tin Bronzes*)
- C95000-C95999: Copper-Aluminum-Iron and Copper-Aluminum-Iron-Nickel Alloys (*Aluminium Bronzes*)

Revision Date: November 20, 2025

Bronzes (C90000 - C95999)

* = are alloys registered with the U.S. EPA as Antimicrobial.

UNS #	Cu		Pb		Sn		Zn		Fe		P		Ni		Al		Mg		Mn		S		Sb		Si		Other Named Elements		Status	
	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%		
C90200	91.0 ⁽¹⁾ ₍₂₎	94.0		0.30	6.0	8.0		0.50		0.20		0.05 ₍₃₎		0.50 ₍₄₎		0.005					0.05		0.20		0.005				active	
C90250 Tin Bronze	89.0	91.0		0.30	9.0	11.0		0.50		0.25		0.05		2.0		0.005				0.20		0.05		0.02		0.005			active	
C90280*	87.0	90.0 ⁽⁵⁾		.09	9.0	11.0			.30	.6		.05									.30	.6							active	
C90300 Tin Bronze	86.0	89.0 ⁽¹⁾⁽²⁾		0.30	7.5	9.0	3.0	5.0		0.20		0.05 ₍₃₎		1.0 ⁽⁴⁾		0.005					0.05		0.20		0.005				active	
C90400* Tin Bronze	86.0 ⁽⁶⁾	89.0		0.09	7.5	8.5	1.0	5.0		0.40		0.05		1.0		0.005				0.01	0.10	0.65		0.02		0.005		0.10 B 0.10 Zr	active	
C90410* Tin Bronze	86.0	89.0 ⁽⁶⁾		0.09	7.5	8.5	1.0	5.0		0.40		0.05		1.0		0.005				0.01	0.20	0.10	0.65		0.02		0.005		0.10 B 0.10 Zr	active

UNS #	Cu		Pb		Sn		Zn		Fe		P		Ni		Al		Mg		Mn		S		Sb		Si		Other Named Elements		Status
	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	
C90420* Tin Bronze	86.0 ⁽⁶⁾	89.0		0.09	7.5	8.5	1.0	5.0		0.40		0.05		1.0						0.20	0.10	0.65		0.02				0.10 B 0.10 C 0.10 Ti 0.10 Zr	active
C90430* Low-Lead Tin Bronze	86.0 ⁽⁶⁾	89.0		0.09	7.5	8.5	1.0	5.0		0.40		0.05		1.0						0.20	0.10	0.65	0.10	1.5				0.10 B 0.10 C 0.10 Ti 0.10 Zr	active
C90500 Gun Metal	86.0	89.0 ⁽⁷⁾⁽¹⁾		0.30	9.0	11.0	1.0	3.0		0.20		0.05 ⁽³⁾		1.0 ⁽⁴⁾		0.005					0.05		0.20		0.005				active
C90700 Tin Bronze, 65	88.0	90.0 ⁽²⁾⁽¹⁾		0.50	10.0	12.0		0.50		0.15		0.30 ⁽³⁾		0.50 ⁽⁴⁾		0.005					0.05		0.20		0.005				active
C90710		Rem ⁽¹⁾ ₍₂₎		0.25	10.0	12.0		0.05		0.10	0.05 ⁽³⁾	1.2		0.10 ⁽⁴⁾		0.005					0.05		0.20		0.005				active
C90800 Tin Bronze	85.0	89.0 ⁽²⁾⁽¹⁾		0.25	11.0	13.0		0.25		0.15		0.30 ⁽³⁾		0.50 ⁽⁴⁾		0.005					0.05		0.20		0.005				active
C90810		Rem ⁽²⁾ ₍₁₎		0.25	11.0	13.0		0.30		0.15	0.15	0.8 ⁽³⁾		0.50 ⁽⁴⁾		0.005					0.05		0.20		0.005				active
C90900	86.0 ⁽¹⁾ ₍₂₎	89.0		0.25	12.0	14.0		0.25		0.15		0.05 ⁽³⁾		0.50 ⁽⁴⁾		0.005					0.05		0.20		0.005				active
C91000	84.0 ⁽²⁾ ₍₁₎	86.0		0.20	14.0	16.0		1.5		0.10		0.05 ⁽³⁾		0.8 ⁽⁴⁾		0.005					0.05		0.20		0.005				active
C91100	82.0 ⁽¹⁾ ₍₂₎	85.0		0.25	15.0	17.0		0.25		0.25		1.0 ⁽³⁾		0.50 ⁽⁴⁾		0.005					0.05		0.20		0.005				active
C91300	79.0 ⁽²⁾ ₍₁₎	82.0		0.25	18.0	20.0		0.25		0.25		1.0 ⁽³⁾		0.50 ⁽⁴⁾		0.005					0.05		0.20		0.005				active
C91500 Copper Tin Alloy		Rem	2.0	3.2	9.0	11.0						0.50	2.8	4.0															inactive 01/73
C91600	86.0	89.0 ⁽²⁾⁽¹⁾		0.25	9.7	10.8		0.25		0.20		0.30 ⁽³⁾	1.2	2.0 ⁽⁴⁾		0.005					0.05		0.20		0.005				active
C91700 Nickel Gear Bronze	84.0 ⁽²⁾ ₍₁₎	87.0		0.25	11.3	12.5		0.25		0.20		0.30 ⁽³⁾	1.2 ⁽⁴⁾	2.0		0.005					0.05		0.20		0.005				active

UNS #	Cu		Pb		Sn		Zn		Fe		P		Ni		Al		Mg		Mn		S		Sb		Si		Other Named Elements		Status
	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	
C92200 Navy M Bronze	86.0 ⁽¹⁾ ₍₆₎	90.0	1.0	2.0	5.5	6.5	3.0	5.0		0.25		0.05 ₍₃₎		1.0 ⁽⁴⁾		0.005					0.05		0.25		0.005				active
C92210	86.0	89.0 ⁽¹⁾⁽⁶⁾	1.7	2.5	4.5	5.5	3.0	4.5		0.25		0.03 ₍₃₎	0.7	1.0 ⁽⁴⁾		0.005					0.05		0.20		0.005				active
C92220 ₍₆₎	86.0 ⁽¹⁾	88.0	1.5	2.5	5.0	6.0	3.0	5.5		0.25		0.05 ₍₃₎	0.50 ⁽⁴⁾	1.0															active
C92300 Leaded Tin Bronze	85.0 ⁽⁶⁾ ₍₁₎	89.0	0.30	1.0	7.5	9.0	2.5	5.0		0.25		0.05 ₍₃₎		1.0 ⁽⁴⁾		0.005					0.05		0.25		0.005				active
C92310		Rem ⁽⁶⁾ ₍₁₎	0.30	1.5	7.5	8.5	3.5	4.5						1.0 ⁽⁴⁾		0.005				0.03					0.005				active
C92400	86.0 ⁽¹⁾ ₍₆₎	89.0	1.0	2.5	9.0	11.0	1.0	3.0		0.25		0.05 ₍₃₎		1.0 ⁽⁴⁾		0.005					0.05		0.25		0.005				active
C92410		Rem ⁽¹⁾ ₍₆₎	2.5	3.5	6.0	8.0	1.5	3.0		0.20				0.20 ⁽⁴⁾		0.005				0.05			0.25		0.005				active
C92500	85.0	88.0 ⁽⁶⁾⁽¹⁾	1.0	1.5	10.0	12.0		0.50		0.30		0.30 ₍₃₎	0.8	1.5 ⁽⁴⁾		0.005					0.05		0.25		0.005				active
C92600 ₍₆₎	86.0 ⁽¹⁾	88.5	0.8	1.5	9.3	10.5	1.3	2.5		0.20		0.03 ₍₃₎		0.7 ⁽⁴⁾		0.005					0.05		0.25		0.005				active
C92610		Rem ⁽¹⁾ ₍₆₎	0.30	1.5	9.5	10.5	1.7	2.8		0.15				1.0 ⁽⁴⁾		0.005				0.03					0.005				active
C92700 Leaded Tin Bronze	86.0	89.0 ⁽⁶⁾⁽¹⁾	1.0	2.5	9.0	11.0		0.7		0.20		0.25 ₍₃₎		1.0 ⁽⁴⁾		0.005					0.05		0.25		0.005				active
C92710		Rem ⁽⁶⁾ ₍₁₎	4.0	6.0	9.0	11.0		1.0		0.20		0.10 ₍₃₎		2.0 ⁽⁴⁾		0.005					0.05		0.25		0.005				active
C92800	78.0 ⁽⁶⁾ ₍₁₎	82.0	4.0	6.0	15.0	17.0		0.8		0.20		0.05 ₍₃₎		0.8 ⁽⁴⁾		0.005					0.05		0.25		0.005				active
C92810	78.0	82.0 ⁽¹⁾⁽⁶⁾	4.0	6.0	12.0	14.0		0.50		0.50		0.05 ₍₃₎	0.8	1.2 ⁽⁴⁾		0.005					0.05		0.25		0.005				active
C92900	82.0	86.0 ⁽⁶⁾⁽¹⁾	2.0	3.2	9.0	11.0		0.25		0.20		0.50 ₍₃₎	2.8	4.0 ⁽⁴⁾		0.005					0.05		0.25		0.005				active
C93100		Rem ⁽⁸⁾ ₍₁₎	2.0	5.0	6.5	8.5		2.0		0.25		0.30 ₍₃₎		1.0 ⁽⁴⁾		0.005					0.05		0.25		0.005				active

UNS #	Cu		Pb		Sn		Zn		Fe		P		Ni		Al		Mg		Mn		S		Sb		Si		Other Named Elements		Status
	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	
C93200	81.0	85.0 ⁽⁸⁾⁽¹⁾	6.0	8.0	6.3	7.5	1.0	4.0		0.20		0.15 ₍₃₎		1.0 ⁽⁴⁾		0.005					0.08		0.35		0.005				active
C93400	82.0 ⁽¹⁾ ₍₈₎	85.0	7.0	9.0	7.0	9.0		0.8		0.20		0.50 ₍₃₎		1.0 ⁽⁴⁾		0.005					0.08		0.50		0.005				active
C93500	83.0 ⁽¹⁾ ₍₈₎	86.0	8.0	10.0	4.3	6.0		2.0		0.20		0.05 ₍₃₎		1.0 ⁽⁴⁾		0.005					0.08		0.30		0.005				active
C93600	79.0	83.0 ⁽⁶⁾	11.0	13.0	6.0	8.0		1.0		0.20		0.15 ₍₃₎		1.0 ⁽⁴⁾		0.005					0.08		0.55		0.005				active
C93700 Bearing Bronze	78.0 ⁽⁸⁾	82.0	8.0	11.0	9.0	11.0		0.8		0.7 ⁽⁹⁾		0.10 ₍₃₎		0.50 ₍₄₎		0.005					0.08		0.50		0.005				active
C93720	83.0 ⁽⁸⁾		7.0	9.0	3.5	4.5		4.0		0.7		0.10 ₍₃₎		0.50 ₍₄₎									0.50						active
C93800 Anti-acid Metal	75.0 ⁽⁸⁾	79.0	13.0	16.0	6.3	7.5		0.8		0.15		0.05 ₍₃₎		1.0 ⁽⁴⁾		0.005					0.08		0.8		0.005				active
C93900 79-6-15	76.5	79.5 ⁽¹⁰⁾	14.0	18.0	5.0	7.0		1.5		0.40		1.5 ⁽³⁾		0.8 ⁽⁴⁾		0.005					0.08		0.50		0.005				active
C94000	69.0	72.0 ⁽¹¹⁾	14.0	16.0	12.0	14.0		0.50		0.25		0.05 ₍₃₎	0.50	1.0 ⁽⁴⁾		0.005					0.08 ₍₁₂₎		0.50		0.005				active
C94100	72.0 ⁽¹¹⁾	79.0	18.0	22.0	4.5	6.5		1.0		0.25		0.50 ₍₃₎		1.0 ⁽⁴⁾		0.005					0.08 ₍₁₂₎		0.8		0.005				active
C94200 Cast High- Leaded Tin Bronze	68.5	75.5	3.0	4.0	3.0	4.0		3.0		0.35				0.50									0.50						inactive 03/92
C94300 Soft Bronze	67.0	72.0 ⁽⁸⁾	23.0	27.0	4.5	6.0		0.8		0.15		0.08 ₍₃₎		1.0 ⁽⁴⁾		0.005					0.08 ₍₁₂₎		0.8		0.005				active
C94310		Rem ⁽⁸⁾	27.0	34.0	1.5	3.0		0.50		0.50		0.05 ₍₃₎	0.25 ₍₄₎	1.0									0.50						active
C94320		Rem ⁽⁸⁾	24.0	32.0	4.0	7.0				0.35																			active
C94330	68.5 ⁽⁸⁾	75.5	21.0	25.0	3.0	4.0		3.0		0.7		0.10 ₍₃₎		0.50 ₍₄₎									0.50						active

UNS #	Cu		Pb		Sn		Zn		Fe		P		Ni		Al		Mg		Mn		S		Sb		Si		Other Named Elements		Status
	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	
C94400		Rem ⁽⁸⁾	9.0	12.0	7.0	9.0		0.8		0.15		0.50 ₍₃₎		1.0 ⁽⁴⁾		0.005					0.08		0.8		0.005				active
C94500		Rem ⁽⁸⁾	16.0	22.0	6.0	8.0		1.2		0.15		0.05 ₍₃₎		1.0 ⁽⁴⁾		0.005					0.08		0.8		0.005				active
C94700* Cast Nickel-Tin Bronze	85.0	90.0 ⁽¹¹⁾		0.09 ₍₁₃₎	4.5	6.0	1.0	2.5		0.25		0.05	4.5 ⁽⁴⁾	6.0		0.005				0.20		0.05		0.15		0.005			active
C94800	84.0 ⁽¹¹⁾	89.0	0.30	1.0	4.5	6.0	1.0	2.5		0.25		0.05	4.5	6.0 ⁽⁴⁾		0.005				0.20		0.05		0.15		0.005			active
C94900	79.0 ⁽²⁾	81.0	4.0	6.0	4.0	6.0	4.0	6.0		0.30		0.05	4.0	6.0 ⁽⁴⁾		0.005				0.10		0.08		0.25		0.005			active
C95200*	86.0 ⁽⁸⁾								2.5	4.0					8.5	9.5													active
C95210*	86.0 ⁽⁸⁾			0.05		0.10		0.50	2.5	4.0				1.0 ⁽⁴⁾	8.5	9.5		0.05		1.0					0.25			active	
C95220*		Rem ⁽⁵⁾							2.5	4.0				2.5 ⁽⁴⁾	9.5	10.5				0.50									active
C95300*	86.0 ⁽⁸⁾								0.8	1.5					9.0	11.0													active
C95400*	83.0 ⁽⁵⁾								3.0	5.0				1.5 ⁽⁴⁾	10.0	11.5				0.50									active
C95410*	83.0 ⁽⁵⁾								3.0	5.0			1.5	2.5 ⁽⁴⁾	10.0	11.5				0.50									active
C95420*	83.5 ⁽⁵⁾								3.0	4.3				0.50 ₍₄₎	10.5	12.0				0.50									active
C95430* Copper Aluminum Iron Alloy		Rem												0.50	10.5	12.0				0.50									inactive 03/92
C95500*	78.0 ⁽⁵⁾								3.0	5.0			3.0	5.5 ⁽⁴⁾	10.0	11.5				3.5									active
C95510*	78.0 ⁽¹⁴⁾					0.20		0.30	2.0	3.5			4.5	5.5 ⁽⁴⁾	9.7	10.9				1.5									active
C95520*	74.5 ⁽⁵⁾			0.03		0.25		0.30	4.0	5.5			4.2	6.0 ⁽⁴⁾	10.5	11.5				1.5						0.15	0.20 Co 0.05 Cr		active
C95600*	88.0 ⁽⁸⁾													0.25 ₍₄₎	6.0	8.0									1.8	3.2			active
C95700*	71.0 ⁽⁵⁾								2.0	4.0			1.5 ⁽⁴⁾	3.0	7.0	8.5				11.0	14.0					0.10			active
C95710*	71.0 ⁽⁵⁾			0.05		1.0		0.50	2.0	4.0		0.05	1.5 ⁽⁴⁾	3.0	7.0	8.5				11.0	14.0					0.15			active

UNS #	Cu		Pb		Sn		Zn		Fe		P		Ni		Al		Mg		Mn		S		Sb		Si		Other Named Elements		Status
	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	
C95720* Copper Aluminum Iron Alloy	73.0 ⁽⁵⁾			0.03		0.10		0.10	1.5	3.5			3.0 ⁽⁴⁾	6.0	6.0	8.0			12.0	15.0						0.10		0.09 Cr	active
C95800*	79.0 ⁽⁵⁾			0.03					3.5 ⁽¹⁵⁾	4.5			4.0	5.0 ⁽¹⁵⁾	8.5	9.5			0.8	1.5						0.10			active
C95810* Cast Aluminum Bronze	79.0 ⁽⁵⁾			0.09				0.50	3.5 ⁽¹⁵⁾	4.5			4.0 ⁽¹⁵⁾	5.0	8.5	9.5		0.05	0.8	1.5						0.10			active
C95815	76.0	82.5 ⁽⁵⁾		0.03		0.10		0.40	4.0	5.5			4.0	5.3	8.8	10.0		0.05		2.5						0.10		0.05 Cr 0.01 Bi	active
C95820*	77.5 ⁽¹⁶⁾			0.02		0.20		0.20	4.0	5.0			4.5	5.8 ⁽⁴⁾	9.0	10.0				1.5						0.10			active
C95900*		Rem ⁽⁵⁾							3.0	5.0				0.50 ⁽⁴⁾	12.0	13.5				1.5									active

* = are alloys registered with the U.S. EPA as Antimicrobial.

(1) = In determining Cu min., Cu may be calculated as Cu + Ni.

(2) = Cu + Sum of Named Elements 99.4% min.

(3) = For continuous castings P shall be 1.5% max.

(4) = Ni value includes Co.

(5) = Cu + Sum of Named Elements 99.5% min.

(6) = Cu + Sum of Named Elements 99.3% min.

(7) = Cu + Sum of Named Elements 99.7% min.

(8) = Cu + Sum of Named Elements 99.0% min.

(9) = Fe shall be 0.35% max. when used for steel-backed bearings

(10) = Cu + Sum of Named Elements 98.9% min.

(11) = Cu + Sum of Named Elements 98.7% min.

(12) = For continuous castings S shall be 0.25% max.

(13) = The mechanical properties of C94700 (heat treated) may not be attainable if the Pb content exceeds 0.01%.

(14) = Cu + Sum of Named Elements 99.8% min.

(15) = Fe content shall not exceed Ni content.

(16) = Cu + Sum of Named Elements 99.2% min.