



Application Datasheet

Standard Designation for Wrought Copper Alloys

Revision Date: November 20, 2025

High Copper Alloys (C16000 - C19999)

* = are alloys registered with the U.S. EPA as Antimicrobial.

UNS #	Cu		Pb		Sn		Zn		Fe		P		Ni		Al		Be		Co		Cr		Si		Other Named Elements		Status
	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	
C16200* Cadmium Copper		Rem ⁽¹⁾⁽²⁾							0.02																0.7 Cd	1.2 Cd	active
C16210* High Copper Alloy		Rem ⁽¹⁾⁽²⁾																							0.50 Cd	1.20 Cd	inactive 03/92
C16400* High Copper Alloy	99.8 ⁽²⁾				0.20	0.40			0.02																0.6 Cd	0.9 Cd	inactive 07/74
C16500*		Rem ⁽¹⁾⁽²⁾			0.50	0.7			0.02																0.6 Cd	1.0 Cd	active
C17000* Copper Beryllium		Rem ⁽²⁾⁽¹⁾													0.20	1.60	1.85	0.20 ⁽³⁾					0.20				active
C17200* Copper Beryllium		Rem ⁽¹⁾⁽²⁾													0.20	1.80	2.00	0.20 ⁽³⁾					0.20				active

UNS #	Cu		Pb		Sn		Zn		Fe		P		Ni		Al		Be		Co		Cr		Si		Other Named Elements		Status
	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	
C17210		Rem ⁽¹⁾⁽²⁾		0.095												0.20	1.80	2.00	0.20 ⁽³⁾					0.20	0.005 Sb 0.005 Bi	0.10 Sb 00.10 Bi	active
C17300 Copper Beryllium		Rem ⁽¹⁾⁽²⁾	0.20	0.6												0.20	1.80	2.00	0.20 ⁽³⁾					0.20			active
C17400* Beryllium Copper		Rem ⁽²⁾⁽¹⁾								0.20 ⁽³⁾						0.20	0.15	0.50	0.15	0.35 ⁽³⁾				0.20			inactive 03/92
C17410* Copper Beryllium		Rem ⁽¹⁾⁽²⁾								0.20						0.20	0.15	0.50	0.35	0.6				0.20			active
C17420* Copper Beryllium		Rem ⁽²⁾								0.20						0.20	0.05	0.15	0.05	0.6				0.20			inactive 03/92
C17450* Copper Beryllium		Rem ⁽¹⁾⁽²⁾				0.25				0.20			0.50	1.0		0.20	0.15	0.50					0.20		0.50 Zr	active	
C17455 Copper Beryllium		Rem ⁽¹⁾⁽²⁾	0.20	0.6		0.25				0.20			0.50	1.0 ⁽⁴⁾		0.20	0.15	0.50					0.20		0.50 Zr	active	
C17460* Copper Beryllium		Rem ⁽¹⁾⁽²⁾				0.25				0.20			1.0	1.4		0.20	0.15	0.50					0.20		0.50 Zr	active	
C17465 Copper Beryllium		Rem ⁽¹⁾⁽²⁾	0.20	0.6		0.25				0.20			1.0 ⁽⁴⁾	1.4		0.20	0.15	0.50					0.20		0.50 Zr	active	
C17500* Copper Beryllium		Rem ⁽²⁾⁽¹⁾								0.10						0.20	0.4	0.7	2.4	2.7				0.20			active
C17510* Copper Beryllium		Rem ⁽¹⁾⁽²⁾								0.10			1.4	2.2		0.20	0.2	0.6		0.3				0.20			active

UNS #	Cu		Pb		Sn		Zn		Fe		P		Ni		Al		Be		Co		Cr		Si		Other Named Elements		Status
	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	
C17520* Copper Beryllium		Rem ⁽²⁾											0.50	1.5			0.10	0.30							0.06 Mg 0.10 Zr	0.30 Mg 0.30 Zr	inactive 03/92
C17530* Copper Beryllium		Rem ⁽²⁾⁽¹⁾							0.20				1.8 ⁽⁴⁾	2.5		0.6	0.20	0.40						0.20			active
C17540 CW103C		Rem ⁽²⁾⁽¹⁾							0.2				0.8	1.3			0.4	0.7	0.8	1.3				0.2			active
C17600* Copper Beryllium		Rem ⁽²⁾							0.10							0.20	0.25	0.50	1.4	1.7					0.9 Ag	1.1 Ag	inactive 03/92
C17700* Copper Beryllium		Rem ⁽²⁾							0.10								0.40	0.70	2.4	2.7				0.20	0.40 Te	0.6 Te	inactive 03/92
C18000		Rem ⁽¹⁾⁽²⁾							0.15				1.8	3.0 ⁽⁴⁾							0.10	0.8	0.40	0.8			active
C18020		Rem ⁽²⁾⁽⁵⁾			0.05	0.25	0.10	0.30													0.10	0.30		0.05			active
C18025 High Copper Alloy		Rem ⁽²⁾⁽⁵⁾			0.15	0.25	0.05	0.15													0.20	0.30	0.03	0.07	0.01 Mg	0.03 Mg	active
C18030		Rem ⁽²⁾⁽⁵⁾			0.08	0.12					0.005	0.015									0.10	0.20					active
C18040		Rem ⁽⁶⁾⁽²⁾			0.20	0.30	0.05	0.15		Rem	0.005	0.015									0.25	0.35					active
C18045	99.1 ⁽⁵⁾⁽²⁾				0.20	0.30	0.15	0.30													0.20	0.35		0.05			active
C18050		Rem ⁽²⁾⁽⁷⁾																			0.05	0.15			0.005 Te	0.015 Te	active
C18060		Rem ⁽⁵⁾				0.10													0.01	0.15	0.20	0.40	0.01	0.15	0.01 Mg	.15 Mg	active
C18070	99.0 ⁽²⁾⁽⁷⁾																				0.15	0.40	0.02	0.07	0.01 Ti	0.40 Ti	active
C18080		Rem ⁽⁸⁾⁽⁷⁾							0.02	0.20											0.20	0.7	0.01	0.10	0.01 Ag 0.01 Ti	0.30 Ag 0.15 Ti	active
C18085		Rem ⁽¹⁾																			0.20	1.0	0.01	0.50	0.01 Ag 0.01 Ti	0.30 Ag 0.8 Ti	active
C18090	96.0 ⁽⁹⁾⁽²⁾				0.50	1.2							0.30	1.2							0.20	1.0			0.15 Ti	0.8 Ti	active

UNS #	Cu		Pb		Sn		Zn		Fe		P		Ni		Al		Be		Co		Cr		Si		Other Named Elements		Status
	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	
C18095		Rem ⁽¹⁾							0.15	0.50											0.6	1.0	0.01	0.12	0.10 Ti	0.40 Ti	active
C18100	98.7 ⁽²⁾⁽¹⁾																				0.40	1.2			0.03 Mg 0.08 Zr	0.06 Mg 0.20 Zr	active
C18135		Rem ⁽²⁾⁽¹⁾																			0.20	0.6			0.20 Cd	0.6 Cd	active
C18140		Rem ⁽²⁾⁽¹⁾																			0.15	0.45	0.005	0.05	0.05 Zr	0.25 Zr	active
C18141 High Copper Alloy MZC1		Rem ⁽²⁾⁽¹⁾				0.20									0.10						0.20	0.40	0.01	0.03	0.002 Mg 0.07 Zr	0.05 Mg 0.13 Zr	active
C18142		Rem ⁽¹⁾⁽¹⁰⁾																			0.20	0.30			0.05 Mg	0.30 Mg	active
C18143 High Copper		Rem ⁽²⁾⁽¹⁾				0.20									0.10						0.20	0.40	0.01	0.03	0.07 Zr	0.05 Mn 0.13 Zr	active
C18145		Rem ⁽¹⁾⁽²⁾					0.10	0.30													0.10	0.30			0.05 Zr	0.15 Zr	active
C18147		Rem ⁽⁵⁾																			0.15	0.35			0.02 Zr	0.05 Zr	active
C18148		Rem ⁽⁹⁾									0.004	0.02									0.50	0.80			0.03 Zr	0.10 Zr	active
C18150		Rem ⁽¹¹⁾⁽²⁾																			0.50	1.5			0.02 Zr	0.20 Zr	active
C18160		Rem ⁽¹¹⁾⁽¹⁰⁾							0.10												0.20	1.20		0.10	0.05 Zr	0.25 Zr	active
C18200 Chromium Copper		Rem ⁽¹⁾⁽²⁾		0.05					0.10												0.6	1.2		0.10			active
C18400 Chromium Copper		Rem ⁽²⁾⁽¹⁾					0.7		0.15		0.05										0.40	1.2		0.10	0.005 As 0.005 Ca 0.05 Li		active
C18500 High Copper		Rem ⁽²⁾		0.015							0.04										0.40	1.0			0.08 Ag	0.12 Ag	inactive 03/92
C18550 Chromium Copper		Rem ⁽²⁾			0.10	0.14															0.6	1.0					inactive 03/92

UNS #	Cu		Pb		Sn		Zn		Fe		P		Ni		Al		Be		Co		Cr		Si		Other Named Elements		Status
	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	
C18600		Rem ⁽²⁾⁽¹⁾							0.25	0.8				0.25						0.10	0.10	1.0			0.05 Ti 0.05 Zr	0.50 Ti 0.40 Zr	active
C18610		Rem ⁽²⁾⁽¹⁾							0.10					0.25					0.25	0.8	0.10	1.0			0.05 Ti 0.05 Zr	0.50 Ti 0.40 Zr	active
C18620* High Copper	99.40 ⁽²⁾				0.03	0.15	0.02	0.10			0.040	0.075	0.02	0.06					0.14	0.21							active
C18625* HRSC	99.40 ⁽²⁾⁽¹⁾				.01	.10		.10			.05	.09		.10					.15	.35							active
C18660* High Copper Alloy		Rem ⁽⁵⁾⁽²⁾				0.08			0.10	0.15	0.03	0.08									0.01	0.02	0.01	0.02	0.03 Mg 0.07 Mg		active
C18661*		Rem ⁽¹⁾⁽²⁾				0.20			0.10	0.001	0.02														0.10 Mg 0.7 Mg		active
C18665*	99.0 ⁽²⁾									0.002	0.04														0.40 Mg 0.9 Mg		active
C18670 MSP5		Rem ⁽¹⁾⁽²⁾																							1.2 Mg 1.9 Mg		active
C18700 Free-Machining Cu	99.5 ⁽²⁾⁽¹²⁾		0.8	1.5																							active
C18835*	99.0 ⁽¹⁾⁽²⁾			0.05	0.15	0.55		0.30		0.10		0.01															active
C18900*		Rem ⁽¹⁾⁽²⁾		0.02	0.6	0.9		0.10				0.05				0.01							0.15	0.40	0.10 Mn 0.30 Mn		active
C18910*		Rem ⁽²⁾										0.15											0.50		0.50 Mn		inactive 12/98
C18980* ⁽¹⁾	98.0 ⁽²⁾			0.02		1.0						0.15											0.50		0.50 Mn		active
C18990		Rem ⁽⁵⁾⁽²⁾			1.8	2.2					0.005	0.015									0.10	0.20					active
C19000*		Rem ⁽²⁾⁽¹⁾		0.05				0.8		0.10	0.15	0.35	0.9	1.3													active
C19002*		Rem ⁽²⁾⁽¹⁾		0.05	0.02	0.30	0.01	0.35		0.10		0.05	1.4	1.7 ⁽⁴⁾									0.20	0.35	0.02 Ag 0.005 Zr	0.50 Ag 0.01 Mg 0.05 Zr	active

UNS #	Cu		Pb		Sn		Zn		Fe		P		Ni		Al		Be		Co		Cr		Si		Other Named Elements		Status
	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	
C19005		Rem ⁽¹⁾⁽²⁾		0.05	0.02	0.30	0.20	0.7		0.10		0.05	1.4 ⁽⁴⁾	1.7									0.20	0.35		0.50 Ag 0.01 Mg 0.08 Zr	active
C19010*		Rem ⁽²⁾⁽¹⁾									0.01	0.05	0.8	1.8									0.15	0.35			active
C19015*		Rem ⁽⁷⁾⁽²⁾									0.02	0.20	0.50	2.4									0.10	0.40	0.02 Mg	0.15 Mg	active
C19020*		Rem ⁽⁷⁾⁽²⁾			0.30	0.9					0.01	0.20	0.50	3.0													active
C19022* High Copper Alloy		Rem ⁽¹⁾⁽²⁾		0.009	0.3	1.0		0.2		0.04	0.01	0.07	0.3	1.0 ⁽⁴⁾													active
C19024* High Copper Alloy		Rem ⁽⁵⁾⁽²⁾		0.01	.02	0.8		0.05		0.02	0.008	0.05	0.10	0.6													active
C19025*		Rem ⁽²⁾⁽¹¹⁾			0.7	1.1		0.20		0.10	0.03	0.07	0.8	1.2													active
C19026		Rem ⁽¹⁾		0.01	0.7	1.1		0.50			0.03	0.07	0.8	1.2									0.07	0.25			active
C19027* NB 115 High Copper		Rem ⁽¹¹⁾⁽²⁾			1.20	1.80		0.20		0.10	0.03	0.15	0.50	1.20												0.20 Mg	active
C19030*		Rem ⁽²⁾⁽¹¹⁾		0.02	1.0	1.5				0.10	0.01	0.03	1.5	2.0													active
C19040* CAC5 High Copper	96.1 ⁽²⁾⁽⁷⁾			0.02	1.0	2.0		0.8		0.06	0.02	0.09	0.7	0.9 ⁽⁴⁾										0.010		0.02 Mn	active
C19050* SPKFC-5E High Copper	95.1 ⁽²⁾⁽⁷⁾			0.02	0.8	2.5		1.0	0.05	0.15	0.08	0.20	0.50 ⁽⁴⁾	1.0													active
C19100		Rem ⁽¹⁾⁽²⁾		0.10				0.50		0.20	0.15	0.35	0.9	1.3											0.35 Te	0.6 Te	active
C19140		Rem ⁽¹⁾⁽²⁾	0.40	0.8		0.05		0.50		0.05	0.15	0.35	0.8	1.2													active
C19150		Rem ⁽¹⁾⁽²⁾	0.50	1.0		0.05				0.05	0.15	0.35	0.8	1.2													active
C19160		Rem ⁽²⁾⁽¹⁾	0.8	1.2		0.05		0.50		0.05	0.15	0.35	0.8	1.2													active

UNS #	Cu		Pb		Sn		Zn		Fe		P		Ni		Al		Be		Co		Cr		Si		Other Named Elements		Status
	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	
C19170* KLF170 High Copper	96.8 ⁽⁷⁾⁽²⁾			0.02		0.8		1.0	0.05	0.15	0.08	0.20	0.50 ⁽⁴⁾	1.0										0.010			active
C19200*	98.5 ⁽⁷⁾							0.20	0.8	1.2	0.01	0.04															active
C19210*		Rem ⁽⁷⁾							0.05	0.15	0.025	0.04															active
C19215*		Rem ⁽⁷⁾					1.1	3.5	0.05	0.20	0.025	0.050															active
C19217		Rem ⁽¹³⁾							0.09	0.20	0.05	0.09													0.05 Mn	0.20 Mn	active
C19220*		Rem ⁽⁷⁾			0.05	0.10			0.10	0.30	0.03	0.07	0.10	0.25											0.005 B	0.015 B	active
C19240* Super KFC	97.5 ⁽⁷⁾			0.02		0.8		1.0	0.15	0.45	0.04	0.20												0.010		0.020 Mn	active
C19250* SPKFC-5W High Copper	95.8 ⁽²⁾⁽⁷⁾			0.02	0.8	2.5		1.0	0.15	0.45	0.04	0.20												0.010		0.02 Mn	active
C19260*	98.5 ⁽⁵⁾								0.40	0.8															0.02 Mg 0.20 Ti	0.15 Mg 0.40 Ti	active
C19280*		Rem ⁽⁷⁾			0.30	0.7	0.30	0.7	0.50	1.5	0.005	0.015															active
C19300* High Copper Alloy	92.0	94.0		0.003		0.03		Rem	2.05	2.60					0.02												inactive 08/73
C19400*	97.0			0.03			0.05	0.20	2.1	2.6	0.015	0.15															active
C19410*		Rem ⁽⁷⁾			0.6	0.9	0.10	0.20	1.8	2.3	0.015	0.050															active
C19419* CAC19 High Copper	96.7 ⁽⁷⁾⁽²⁾			0.02	0.05	0.18	0.10	0.40	1.7	2.3		0.03		0.04 ⁽⁴⁾									0.03	0.09		0.04 Mn	active
C19450*		Rem ⁽⁷⁾			0.8	2.5			1.5	3.0	0.005	0.05															active
C19500*	96.0 ⁽⁷⁾			0.02	0.10	1.0		0.20	1.0	2.0	0.01	0.35				0.02			0.30	1.3							active
C19520	96.6 ⁽⁷⁾		0.01	3.5					0.50	1.5																	active

UNS #	Cu		Pb		Sn		Zn		Fe		P		Ni		Al		Be		Co		Cr		Si		Other Named Elements		Status
	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	Min%	Max%	
C19600* High Copper Alloy		Rem						0.35	0.9	1.2	0.25	0.35															inactive 03/92
C19700*		Rem ⁽⁷⁾		0.05		0.20		0.20	0.30	1.2	0.10	0.40		0.05						0.05						0.01 Mg 0.20 Mg 0.05 Mn	active
C19710*		Rem ⁽¹⁾		0.05		0.20		0.20	0.05	0.40	0.07	0.15		0.10 ⁽⁴⁾												0.03 Mg 0.06 Mg 0.05 Mn	active
C19720*		Rem ⁽¹⁾		0.05		0.20		0.20	0.05	0.50	0.05	0.15		0.10 ⁽⁴⁾												0.06 Mg 0.20 Mg 0.05 Mn	active
C19750*		Rem ⁽⁷⁾		0.05	0.05	0.40		0.20	0.35	1.2	0.10	0.40		0.05						0.05						0.01 Mg 0.20 Mg 0.05 Mn	active
C19800*		Rem ⁽⁷⁾			0.10	1.0	0.30	1.5	0.02	0.50	0.01	0.10														0.10 Mg 1.0 Mg	active
C19810* Hig Copper Alloy		Rem ⁽⁷⁾					1.0	5.0	1.5	3.0		0.10									0.09					0.10 Mg 0.10 Ti 0.10 Zr	active
C19900*		Rem ⁽¹⁾																								2.9 Ti 3.5 Ti	active
C19910* NKT 322 High Copper		Rem ⁽¹⁾							0.17	0.23																2.9 Ti 3.4 Ti	active
C19920		Rem ⁽¹⁾		0.05											0.01	0.30										2.5 Ti 0.01 Nb 3.5 Ti 0.30 Nb	active
C19940 YCuT-AX		Rem ⁽¹⁾							0.05	0.20					0.50	1.5										2.5 Ti 3.5 Ti	active
C19950		Rem ⁽¹⁾																								3.5 Ti 4.5 Ti	active

* = are alloys registered with the U.S. EPA as Antimicrobial.

- (1) = Cu + Sum of Named Elements 99.5% min.
- (2) = Cu value includes Ag.
- (3) = Ni + Co 0.20% min.: Ni + Fe + Co 0.6% max.
- (4) = Ni value includes Co.
- (5) = Cu + Sum of Named Elements 99.9% min.
- (6) = Includes oxygen-free or deoxidized grades with deoxidizers (such as phosphorus boron lithium or others in an amount agreed upon).
- (7) = Cu + Sum of Named Elements 99.8% min.

(8) = Not including Ag.

(9) = Cu + Sum of Named Elements 99.85% min.

(10) = Includes Ag.

(11) = Cu + Sum of Named Elements 99.7% min.

(12) = Includes Pb.

(13) = Cu + Sum of Named Elements, 99.95% min.